

abitex

abitex srl
via del cristo 84
33044 manzano
ud - italy

t +39 0432 746060
www.abitex.eu
info@abitex.eu

grisù 04038



IT
codice doganale
54072011.

utilizzo
tende, imbottiti, assorbimento acustico.

caratteristiche
68% poliestere - 32% polipropilene, altezza cm ± 140,
peso ± 400 gr/m².

tintura
il prodotto è tinta in massa, il prodotto è tinta in filo.

lunghezza pezza
circa 35 mtl.

abrasione
> 135.000 cicli, ISO 12947-2.

solidità alla luce
> 6, ISO 105 B02.

solidità allo sfregamento
secco 4/5, umido 4, ISO 105 X12.

resistenza alla cucitura
ordito 3 mm, trama 3 mm, ISO 13936-2.

pilling
4/5, ISO 12945-2.

resistenza al fuoco
1IM - UNI 9175; classe 1 - UNI 9177;
EN 13773 - Class 1; EN 1021 1/2; BS 5852 part 1;
BS 5852 crib 5 con trattamento, solo su richiesta,
min 200 mt; DIN 4102 B1; NF D 60 013;
California TB 117-2013; IMO FTP Code 307 part 8;
IMO FTP Code 307 part 7; OMORM B1/Q1.

attenzione
sono ammesse leggere differenze di colore tra differenti
partite, non ci assumiamo nessuna responsabilità per il
trasferimento di colore/pigmenti causato da abbigliamento
e accessori.

EN
customs code
54072011.

use
curtains, upholstered furniture, sound absorption.

features
68% polyester - 32% polypropylene, width cm ± 140,
weight ± 400 g/m².

dyeing
solution dyed product, yarn dyed product.

roll length
approx. 35 lm.

abrasion resistance
> 135.000 rubs, ISO 12947-2.

colour fastness to light
> 6, ISO 105 B02.

fastness to rubbing
dry 4/5, wet 4, ISO 105 X12.

seam slippage
warp 3 mm, weft 3 mm, ISO 13936-2.

pilling
4/5, ISO 12945-2.

fire resistance
1IM - UNI 9175; classe 1 - UNI 9177; EN 13773 - Class 1;
EN 1021 1/2; BS 5852 part 1; BS 5852 crib 5 with treatment,
only upon request, min 200 m; DIN 4102 B1; NF D 60 013;
California TB 117-2013; IMO FTP Code 307 part 8;
IMO FTP Code 307 part 7; OMORM B1/Q1.

attention
slight colour differences between different batches are
allowed, we assume no responsibility for the transfer of
colour/pigment caused by clothing and accessories.



fireproof



imo-med



sound
absorbent